Harold S. Bernstein

Editor

Tissue Engineering in Regenerative Medicine

Humana Press

Editor

Harold S. Bernstein
Cardiovascular Research Institute
Eli and Edythe Broad Center of Regeneration Medicine
and Stem Cell Research, Department of Pediatrics
University of California San Francisco
San Francisco, CA, USA
harold.bernstein@ucsf.edu

ISBN 978-1-61779-321-9

e-ISBN 978-1-61779-322-6

DOI 10.1007/978-1-61779-322-6

Springer New York Dordrecht Heidelberg London

Library of Congress Control Number: 2011934681

© Springer Science+Business Media, LLC 2011

All rights reserved. This work may not be translated or copied in whole or in part without the written permission of the publisher (Humana Press, c/o Springer Science+Business Media, LLC, 233 Spring Street, New York, NY 10013, USA), except for brief excerpts in connection with reviews or scholarly analysis. Use in connection with any form of information storage and retrieval, electronic adaptation, computer software, or by similar or dissimilar methodology now known or hereafter developed is forbidden.

The use in this publication of trade names, trademarks, service marks, and similar terms, even if they are not identified as such, is not to be taken as an expression of opinion as to whether or not they are subject to proprietary rights.

Printed on acid-free paper

Humana Press is part of Springer Science+Business Media (www.springer.com)

Preface

Over the past decade, significant advances in the fields of stem cell biology, bioengineering, and animal models have converged on the discipline of regenerative medicine. Significant progress has been made leading from preclinical studies through phase 3 clinical trials for some therapies. This volume provides a state-of-the-art report on tissue engineering toward the goals of tissue and organ restoration and regeneration. Examples from different organ systems illustrate progress with growth factors to assist in tissue remodeling; the capacity of stem cells for restoring damaged tissues; novel synthetic biomaterials to facilitate cell therapy; transplantable tissue patches that preserve three-dimensional structure; synthetic organs generated in culture; aspects of the immune response to transplanted cells and materials; and suitable animal models for nonhuman clinical trials.

Tissue regeneration, and even stem cell therapy, is not a new concept. As discussed in the cautionary first chapter, efforts toward bone and marrow transplantation have been underway for almost half a century. Steady progress has been made in understanding the criteria for successful cell transplantation, and developing a robust structure for clinical oversight. More recently, pluripotent stem cells, with their capacity for self-renewal and tissue-specific differentiation, have become a prime candidate for tissue engineering and regenerative therapies. More than 100 clinical trials have examined the use of mesenchymal stem/stromal cells. Biochemical and mechanical interactions between the extracellular matrix and cell surface receptors, as well as physical interactions between cells, are now recognized as essential for stem cell self-renewal and differentiation. New technologies for scaffold engineering and fabrication have taken advantage of these observations, and hold promise for repairing tissues requiring a highly specialized niche, such as skeletal muscle. These discoveries have led to clinical trials with bioengineered vascular conduits in children with congenital heart disease, complete hollow organs, and complex organs such as bioartificial livers. An evolving understanding of innate and adaptive immune responses, including the foreign body response, has led to novel approaches to modulating the immune system that facilitate tissue repair. Finally, the development of small animal models for discovery, and large animal models for studies of safety and efficacy, has propelled the field of tissue engineering toward the clinic.

The chapters of this book are organized into six sections: Stem Cells, Biomaterials and the Extracellular Environment, Engineered Tissue, Synthetic Organs, Immune Response, and Animal Models. Each section is intended to build upon information presented in the previous chapters, and set the stage for subsequent sections. Throughout the chapters, the reader will observe a common theme of basic discovery informing clinical translation, and clinical studies in animals and humans guiding subsequent experiments at the bench.

I thank the members of my laboratory for their helpful discussion, and my colleagues in Pediatric Cardiology for their support – we all strive to improve the lives of our patients. I appreciate always the encouragement I receive from Tricia Foster, Nathaniel Bernstein, and Katharine Bernstein. I am grateful to the 54 colleagues who have contributed their expertise to this project. We hope that this first edition of *Tissue Engineering and Regenerative Medicine* will serve as an introduction and guide for students of the field at all levels.

San Francisco, CA

Harold S. Bernstein

Contents

Part I Stem Cells

- 1 **Hematopoietic Stem Cell Transplantation:
Reflections on Yesterday and Thoughts for Tomorrow** 3
Andrew D. Leavitt
- 2 **Human Embryonic Stem Cells in Regenerative Medicine** 17
Odessa Yabut and Harold S. Bernstein
- 3 **Current Status of Induced Pluripotent Stem Cells** 39
Thach-Vu Ho, Grace Asuelime, Wendong Li, and Yanhong Shi
- 4 **Mesenchymal Stromal Cells: Latest Advances** 53
Sowmya Viswanathan and Armand Keating

Part II Biomaterials and the Extracellular Environment

- 5 **The Role of Mechanical Forces in Guiding
Tissue Differentiation** 77
Sean P. Sheehy and Kevin Kit Parker
- 6 **Synthetic Multi-level Matrices for Bone Regeneration** 99
Nicholas R. Boyd, Richard L. Boyd, George P. Simon,
and David R. Nisbet
- 7 **Directing Cell Fate Through Biomaterial Microenvironments.....** 123
Kelly Clause, Jonathan Lam, Tatiana Segura, and Thomas H. Barker

Part III Engineered Tissue

- 8 **Basic Considerations with Cell Sheets** 143
Masayuki Yamato and Sebastian Sjöqvist

9 Myocardial Repair and Restoration	161
Sharon S.Y. Wong and Harold S. Bernstein	
10 Skeletal Muscle Engineering: The Need for a Suitable Niche	197
Frédéric Trenz, Anthony Scimè, and Guillaume Grenier	
11 Restoring Blood Vessels	211
Narutoshi Hibino, Christopher Breuer, and Toshiharu Shinoka	
12 Engineering Functional Bone Grafts	221
Sarindr Bhumiratana and Gordana Vunjak-Novakovic	
13 Engineering Functional Cartilage Grafts	237
Andrea R. Tan and Clark T. Hung	
14 Adult Stem Cells and Regeneration of Adipose Tissue	251
Daniel A. Hägg, Bhranti Shah, and Jeremy J. Mao	
 Part IV Synthetic Organs	
15 Hollow Organ Engineering	273
Anthony Atala	
16 Engineering Complex Synthetic Organs	297
Joan E. Nichols, Jean A. Niles, and Joaquin Cortiella	
17 Liver Regeneration and Tissue Engineering	315
Ji Bao, James Fisher, and Scott L. Nyberg	
 Part V Immune Response	
18 Immune Modulation for Stem Cell Therapy	335
Gaetano Faleo and Qizhi Tang	
19 Regenerative Medicine and the Foreign Body Response	353
Kerry A. Daly, Bryan N. Brown, and Stephen F. Badylak	
 Part VI Animal Models	
20 Small Animal Models of Tissue Regeneration	379
Fernando A. Fierro, J. Tomas Egana, Chrisoula A. Toupadakis, Claire Yellowley, Hans-Günther Machens, and Jan A. Nolte	
21 Use of Large Animal and Nonhuman Primate Models for Cell Therapy and Tissue Engineering	393
Alice F. Tarantal and Karina H. Nakayama	
 About the Editor	415
 Index	417

Contributors

Grace Asuelime Department of Neurosciences, Center for Gene Expression and Drug Discovery, Beckman Research Institute of City of Hope, Duarte, CA, USA

Anthony Atala Wake Forest Institute for Regenerative Medicine, Wake Forest University School of Medicine, 5th Floor, Watlington Hall, Medical Center Boulevard, Winston-Salem, NC 27157, USA

Stephen F. Badylak McGowan Institute for Regenerative Medicine, University of Pittsburgh, 450 Technology Drive, Suite 300, Pittsburgh, PA, USA

Ji Bao Mayo Clinic, Rochester, MN, USA

Thomas H. Barker The Wallace H. Coulter Department of Biomedical Engineering at Georgia Tech, Emory University, 313 Ferst Drive, Atlanta, GA 30332, USA

Harold S. Bernstein Cardiovascular Research Institute, University of California San Francisco, Eli and Edythe Broad Center of Regeneration Medicine and Stem Cell Research, Department of Pediatrics, University of California San Francisco, San Francisco, CA 94143-1346, USA

Sarindr Bhumiratana Department of Biomedical Engineering, Columbia University, New York, NY, USA

Nicholas R. Boyd Department of Materials Engineering, Monash University, Clayton, VIC, Australia

Richard L. Boyd Monash Immunology and Stem Cell Laboratories, Monash University, Clayton, VIC, Australia

Christopher Breuer Department of Cardiac Surgery, Interdepartmental Program in Vascular Biology and Therapeutics, Yale University School of Medicine, New Haven, CT, USA

Bryan N. Brown Department of Clinical Sciences, Cornell University, Ithaca, NY, USA

Kelly Clause The Wallace H. Coulter Department of Biomedical Engineering at Georgia Tech, Emory University, Atlanta, GA, USA

Joaquin Cortiella Laboratory of Regenerative and Nano-Medicine, Department of Anesthesiology, University of Texas Medical Branch, Galveston, TX, USA

Kerry A. Daly McGowan Institute for Regenerative Medicine, University of Pittsburgh, Pittsburgh, PA, USA

J. Tomas Egana Department of Plastic and Hand Surgery, University Hospital Rechts der Isar, Technical University of Munich, Munich, Germany

Gaetano Faleo Department of Surgery, University of California, San Francisco, CA, USA

Fernando A. Fierro Department of Internal Medicine, Stem Cell Program and Institute for Regenerative Cures, University of California, Davis, CA, USA

James Fisher Mayo Clinic, Rochester, MN, USA

Guillaume Grenier Étienne-Lebel Clinical Research Center, Department of Orthopedic Surgery, Université de Sherbrooke, 3001-12th Avenue North, J1H 5N4, Sherbrooke, QC, Canada

Daniel A. Hägg Tissue Engineering and Regenerative Medicine Laboratory, Columbia University Medical Center, New York, NY, USA

Narutoshi Hibino Department of Cardiac Surgery, Interdepartmental Program in Vascular Biology and Therapeutics, Yale University School of Medicine, New Haven, CT, USA

Thach-Vu Ho Department of Neurosciences, Center for Gene Expression and Drug Discovery, Beckman Research Institute of City of Hope, Duarte, CA, USA

Clark T. Hung Department of Biomedical Engineering, Columbia University, 1210 Amsterdam Avenue, Engineering Terrace 351, New York, NY 10027, USA

Armand Keating Cell Therapy Program, Princess Margaret Hospital, University Health Network, 610 University Avenue, Suite 5-303, Toronto, ON M5G 2M9, Canada

Department of Medicine, University of Toronto, Toronto, ON, Canada

Jonathan Lam Department of Biomedical Engineering, University of California, Los Angeles, CA, USA

Andrew D. Leavitt Departments of Laboratory Medicine and Medicine, UCSF Adult Blood and Marrow Transplant Laboratory, University of California, 513 Parnassus Avenue, Box 0100, San Francisco, CA 94143-0100, USA

Wendong Li Department of Neurosciences, Center for Gene Expression and Drug Discovery, Beckman Research Institute of City of Hope, Duarte, CA, USA

Hans-Günther Machens Department of Plastic and Hand Surgery, University Hospital Rechts der Isar, Technical University of Munich, Munich, Germany

Jeremy J. Mao Tissue Engineering and Regenerative Medicine Laboratory, Columbia University Medical Center, 630 W. 168 St. – PH7 East, New York, NY 10032, USA

Karina H. Nakayama Departments of Pediatrics, Cell Biology and Human Anatomy, School of Medicine, UC Davis Clinical and Translational Science Center, California National Primate Research Center, University of California, Davis, CA, USA

Joan E. Nichols Laboratory of Regenerative and Nano-Medicine, Departments of Internal Medicine and Infectious Diseases, University of Texas Medical Branch, Galveston, TX, USA

Jean A. Niles Laboratory of Regenerative and Nano-Medicine, University of Texas Medical Branch, Galveston, TX, USA

David R. Nisbet Research School of Engineering, ANU College of Engineering and Computer Science, The Australian National University, Ian Ross Building 31, North Road, Acton, Canberra, ACT 0200, Australia

Jan A. Nolte Department of Internal Medicine, Stem Cell Program and Institute for Regenerative Cures, University of California, Davis, 2921 Stockton Blvd., Room 1300, Sacramento, CA 95817, USA

Scott L. Nyberg Mayo Clinic, 200 First Street SW, Rochester, MN 55905, USA

Kevin Kit Parker Disease Biophysics Group, Wyss Institute for Biologically Inspired Engineering, School of Engineering and Applied Sciences, Harvard University, Pierce Hall, Room 321, 29 Oxford St., Cambridge, MA 02138, USA

Anthony Scimè Muscle Health Research Centre, York University, Toronto, ON, Canada

Tatiana Segura Department of Chemical and Biomolecular Engineering, University of California, Los Angeles, CA, USA

Bhranti Shah Tissue Engineering and Regenerative Medicine Laboratory, Columbia University Medical Center, New York, NY, USA

Sean P. Sheehy Disease Biophysics Group, Wyss Institute for Biologically Inspired Engineering, School of Engineering and Applied Sciences, Harvard University, Cambridge, MA, USA

Chapter 6

Synthetic Multi-level Matrices for Bone Regeneration

Nicholas R. Boyd, Richard L. Boyd, George P. Simon, and David R. Nisbet

Abstract Current bone replacement strategies are clinically inadequate, yet there is great promise in the use of synthetic adjuvant matrices. Electrospinning provides a three-dimensional platform in which matrices can be designed to mimic features of the extracellular matrix and improve bone regeneration. Composite nanofibers can be functionalised with therapeutic molecules, and/or may permit the delivery of growth factor combinations as required to stimulate bone healing. Collectively, these should more precisely direct repair by exogenous and endogenous stem and progenitor cells. The real novelty will be in combining multiple levels of scaffold-based tissue engineering developments in an "off the shelf" clinic-ready product. Until then, application of bioactive nanofiber analogues, with dual-scale three-dimensional porosity that can be co-interfaced within effective stem cell treatment regimes, will be crucial in developing smart matrices for skeletal repair. This review presents holistic concepts for more effective bone regeneration and the methods in which they can be incorporated into nanotechnology-based scaffolds from a materials engineering perspective.

Abbreviations

ALP	Alkaline phosphate
BMP-2	Bone morphogenetic protein-2
BMSCs	Bone-marrow-derived stromal cells
BSP	Bone sialoprotein-2
ECM	Extracellular matrix
FAP	Fluoroapatite

D.R. Nisbet (✉)

Research School of Engineering, ANU College of Engineering and Computer Science,
The Australian National University, Canberra, ACT, Australia

e-mail: david.nisbet@anu.edu.au

FDA	Food and Drug Administration
FGF-2	Fibroblast growth factor-2
HAp	Hydroxyapatite
Hep	Heparin
Hep-S	Heparan sulphate
LbL	Layer-by-layer
MMT	Montmorillonite
MSCs	Mesenchymal stem cells
MWCNT	Multi-walled carbon nanotube
MWNT	Multi-walled nanotube
OC	Osteocalcin
OP	Osteopontin
OPG	Osteoprotegerin
PCL	Poly(ϵ -caprolactone)
PDGF	Platelet-derived growth factor
PEO	Polyethylene oxide
P _{DL} LA	Poly(_{DL} lactide)
PGA	Polyglycolic acid
PLA	Poly(lactic acid)
P _L LA	Poly-L-lactide acid
RANKL	Receptor activator of NF- κ B ligand
RGD	Arg-Gly-Asp
rhBMP-2	Recombinant human BMP-2
SBF	Simulated body fluid
SEM	Scanning electron microscopy
SIS	Small intestinal submucosa
SPARC	Osteonectin
TCP	Tricalcium phosphate
TEM	Transmission electron microscopy
TGF- β	Transforming growth factor β
TSP	Thrombospondin
VEGF	Vascular endothelial growth factor

6.1 Introduction

One of the ironies of improvements to general health and living conditions that lead to an increase in average life span is a higher incidence of skeletal disease. While some treatments do exist, they are usually problematic due to a lack of long-term success and insufficient clinical efficacy. More sophisticated approaches, such as artificial bone substitutes, are thus required on a global scale. The rapidly evolving interface between nanotechnology and biological sciences provides an optimistic outlook.

Bone-related diseases, skeletal abnormalities and physical trauma can often lead to defective skeletal support, such that bone may no longer be able to regenerate and

repair naturally [1]. Osteoporosis, osteonecrosis, bone cancer, osteoarthritis, rickets, Paget's disease and osteogenesis imperfecta [2–8] cause an enormous strain economically and on the patients quality of life. In 1997, it was estimated that osteoporosis affected 75 million people in Europe, USA and Japan alone [9], with alarming projections estimating that the incidence in hip fracture as a result of osteoporosis will double by 2025 [10]. Throughout orthopaedics, neurosurgery and dentistry, some 2.2 million bone-graft surgeries are already performed annually [11]. Two major issues are rapidly becoming clear: (1) the need for bone grafts is increasing and (2) the longevity of existing bone-graft therapies needs to improve in order to avoid revision surgery and to accommodate the expected increase in patient lifespan post-surgery [12, 13]. Consequently, new strategies and more sophisticated materials are required for restoration of bone/joint functionality.

Current bone grafts are burdened by limited availability, infection and morbidity, poor mechanical properties and over-elevated bone resorption [1, 14]. While the traditional "gold standard" autograft has shown a degree of clinical success, only small skeletal defects can be treated and they are very invasive [14]. Alternatively, problems with allografts are compounded by immune rejection, and immunosuppressive drugs carry the added risk of susceptibility to infection [1, 15]. Synthetic biomaterials have provided an alternative solution with advantages in availability, versatility, precision, reduced immune rejection and the potential for smarter, biologically instructive and active bone-graft templates. Most common hard orthopaedic biomaterials, e.g., titanium hip implants, are largely bio-inert which leads to limited integration with endogenous tissue and poorly sustained functional restoration [16]. Numerous attempts to improve the integration of the implant via surface treatment of the titanium [17] have included mechanical roughening, chemical treatment, sol-gel coating, ion implantation and thermal spraying of HAp. However, major limitations still persist and the ability to achieve appropriate mechanical and biological properties has yet to be achieved simultaneously.

Potentially, the most promising fabrication technique for the next generation of synthetic bone grafts is electrospinning. This provides a simple, yet highly versatile bottom-up approach [18], in which a vast array of porous nanofiber matrices can be manufactured by accelerating a jet of charged polymeric liquid under the presence of an electric field [19–21]. A wide range of polymeric, ceramic and composite nanofibers can be produced via electrospinning [18]. In turn, the diversity of electrospun membrane properties and functionality can be manipulated relatively easily. Electrospun fibers are amenable to post-processing surface treatments including deposition of bioactive nanoparticles, attachment of growth factors and bioactive proteins. However, while the approach is simple, the physical science behind electrospinning is quite complex [20, 21] and difficult to control. The challenge is clear: can innovative new strategies be developed to optimise the utility and function of three-dimensional tissue analogues?

Currently, the mechanical properties of electrospun scaffolding for bone tissue engineering are generally inadequate for therapeutic applications as load bearing bone-graft substitutes. While their *in vivo* implementation is in its infancy, direct avenues for their clinical application exist and have advanced as guided-bone-regeneration membranes in areas such as dental restoration. Moreover, augmentation in non-union/delayed fracture healing and in replacement of segmental gap defects

may support revolutionary therapeutic advances if improvements can be made to tailor their mechanical properties.

This review firstly introduces basic bone biology and healing redevelopment processes as a platform for scaffold design. A hierarchy of physical and biochemical inputs have been utilised for stimulating bone regeneration, yet have not been successfully co-incorporated to date. Hence, the focus of this review discusses the most recent, novel and promising advances in scaffold engineering designed primarily for bone tissue reconstruction. Effective three-dimensional synthetic biomatrices for bone regeneration are thought to require surface and structural biomimicry, in conjunction with effective stem cell treatment strategies.

6.2 The Platform for Design: Biology

The successful growth of cells on synthetic matrices is dependent on synergies between topographical, biochemical and mechanical stimuli that best reflect the in vivo microenvironment. Understanding these biological functions, structures and healing processes is therefore crucial for creating relevant inputs into the adjuvant bone graft. Material engineering strategies alone have not yet progressed to the point where they can recreate bone analogues accurately, due to the dynamic nature and intricate hierarchy of bone.

6.2.1 Bone Structure

Bone is a highly organised connective tissue that principally provides structural support for skeletal motion, protection of internal organs and a mineral reservoir for homeostasis of chiefly calcium and phosphate [22–24]. Furthermore, bone supports the primary production of blood cells via haematopoiesis [16], has unique self-regenerative capabilities [25] and an exceptional light-weight combination of strength, stiffness, fatigue resistance, fracture toughness and porosity [26, 27]. The specialised physical and biological capabilities of bone are founded on the complex ECM hierarchy (reviewed in refs. [26, 28]) and subsequent dynamic relationship with bone-associated cells.

At the nanoscale, intricately organised mineralised collagen fibrils (individual fibril (1.5–3.5 nm), fibers (50–70 nm), and bundles of fibers (150–250 nm) [26] form the building blocks of the ECM. A complex, interpenetrative and cooperative network of organic and inorganic components underpins the highly advanced mechanical properties of bone at all scale lengths [26, 29–31]. Bone-apatite nanoplatelets based around the chemical structure of HAp, $\text{Ca}_5(\text{PO}_4)_3\text{OH}$, occupy approximately 70 wt% of bone [32] and are dispersed throughout a highly organised and cross-linked [33, 34] periodic stacking [26, 30, 34] of triple helical collagen type I molecules [31, 35], referred to as tropocollagen. HAp platelets act

as stiffening components and mineral reservoirs, and have been reported to be located on the fiber surface, as well as within the fiber [36, 37]. The organic component makes up about 25 wt% of bone [32], with more than 90% being collagen type I [28]. A small fraction of type V collagen coexists, which facilitates the assembly of fibrillar structures [38, 39], as do several non-collagenous proteins [40]. While only accounting for a minor contribution (approximately 10% [28]) [41], OC [42], SPARC [43, 44], fibronectin [44], BSP [45] and TSP [46–48] play crucial biochemical roles in the ECM.

6.2.2 Bone Maintenance and Remodelling

Bone, like most tissues, undergoes continual self-renewal and requires repair and remodelling following damage. Homeostatic maintenance of bone structure essentially involves a continuing flux between bone resorption by osteoclasts and reformation by osteoblasts, which is initiated through mechanical stimuli and ECM-cellular communication. Osteoclasts are bone-resorbing macrophage-cells, which locally secrete hydrochloric acid that facilitates localised mineral dissolution, followed by up-regulation of cysteine-proteinases (importantly cathepsin K) that degrade the organic matrix [49, 50]. Osteoblasts are bone-forming cells derived from MSCs which are present predominantly in the endosteal niche and surrounding marrow vasculature [51]. New bone is developed through osteoblastic synthesis, deposition, mineralisation and organisation of the ECM. This includes production and secretion of type I collagen, bone apatite and a vast variety of non-collagenous proteins [40], cytokines and growth factors [24, 52].

Virtually all tissues derive growth and differentiation occurs through dynamic interaction with the surrounding ECM. Bone, however, displays uniquely adaptive properties, as the cells and bone remodelling is distinctly sensitive to mechanical stress [53]. Physical forces imposed on bone are translated and interpreted via three-dimensional osteocyte networks through mechanotransduction (ECM-cell cross-talk) [54], which correspondingly feeds instructive signals to regulate osteoblastic and osteoclastic behaviour [53]. On a molecular basis, the structure of bone converges around two key molecules: OPG and OPG-ligand, also known as RANKL [55]. With structural damage to the ECM, including tropocollagen uncoiling, fibrillar sliding and tearing, generation of microcracks, lamellar sliding [34] and macroscopic fracture, new remodelled bone is required.

6.2.3 Bone Healing

Bone healing is complex. A highly regulated sequence of multi-tissue activated events, referred to as the regeneration cascade, proceeds at the initial point of healing. Overlapping of each developmental stage occurs, with multiple cell types and signal

cascades acting in harmony [56, 57]. Unlike soft-tissue healing, bone healing does not leave an obvious scar, the process being regenerative, rather than solely reparative [32, 58, 59]. There are direct links between the mechanisms involved in initial skeletal tissue formation and the fracture healing cascade [60]. Fracture size and mechanical stability are crucial in defining the success of the healing mechanism [61].

The intricacies and multiple-tissue development involved in secondary bone healing have yet to be effectively incorporated in synthetic bone tissue engineering scaffolds. It is thought that the endogenous healing mechanisms activated in response to bone-graft implantation follow similar progressive regeneration as are involved in fracture repair. Indeed understanding the involvements that the various components play in fracture healing is a key feature for designing relevant scaffolds for bone grafts. Bone fracture is followed by an inflammatory response that involves haematoma formation, recruitment of MSCs and activation of inflammatory signals and osteogenic stimulators. A temporary cartilaginous matrix replaces the initial haematoma in order to stabilise the fracture site, which is crucial for facilitating subsequent angiogenesis and primary bone formation. Finally, the woven primary bone fracture callus is reorganised into functional bone. The biological processes, cellular involvement and predominating growth factors involved in each stage of bone regeneration have been previously reviewed in detail [56, 57, 62–64]. Many of these growth factors have successfully been incorporated into synthetic adjuvant scaffolding with therapeutic stimulation of bone repair.

6.3 Levels of Matrix Sophistication

The evolving forefront of nanotechnologies, cellular and molecular microbiology and biomaterial science provides locus for developing highly effective tissue engineering materials on a range of size scales. Each level of sophistication provides an essential biomimetic design input to assist in instructing and stimulating the *in vivo* cellular niche.

6.3.1 *Electrospun Fibers*

6.3.1.1 Natural and Synthetic-Based Polymeric Nanofibers

Electrospun fibers alone are by no means ideal for biomatrices, despite some preliminary success in bone tissue engineering [65]. They are, however, of crucial importance as they form the base-framework in the design of advanced bone tissue constructs since they are morphologically and dimensionally similar to collagen in the endogenous ECM. Initial studies were based on this premise and made important contributions to the mimetic prototypes.

Investigation of cellular response on different fiber diameters have lead to a variety of results [66–70], few of which have been well substantiated [71].

Cellular preference to fiber size is intrinsically difficult to isolate, as with changes in electrospun fiber size, there is subsequent change in the inter-fiber spacing [72, 73], mechanical properties [74] and biodegradability; all of which have been shown to mediate cellular behaviour and underpin the entire performance of the synthetic bone graft. Furthermore, depending on the cell phenotype, preferential fiber size and porosity for maximum cell adhesion may peak at multiple points [71]. It has been well shown that osteoblastic cells respond more favourably to nano-topographic cues demonstrating superior cellular adhesion, growth, proliferation and differentiation [75], similarly seen with co-incorporating nanofibers in microporous scaffolds [73, 76]. Interestingly, cellular behaviour on nanofibers was improved with enhanced levels of bio-stimulative factors in the culture medium [68, 69], thus suggesting synergistic interactions and the necessity for multiple microenvironmental inputs to satisfy the cellular niche.

More recent developments have focussed on advanced electrospun systems and the incorporation of bone-specific bioactivity. As bone has the inherent capacity to regenerate, biodegradable materials have been predominately used. Synthetic polymers, most commonly polyesters (PLA, PGA, PCL, etc.) and their various copolymers, offer the advantage of substantial flexibility in electrospinning processability, mechanical modification, biodegradability and are of relatively low expense. Furthermore, of clinical translational importance, many have FDA-approved biocompatibility and have been widely investigated in other areas of tissue engineering and medical applications. Polymers, such as PCL, have the capacity to be synchronised with the redevelopment rate of endogenous bone *in vivo*, and the degradation by-products do not overly increase the cellular microenvironment acidity [77], making it a more viable solution for sustained cellular mobilisation and angiogenesis [77]. However, most synthetic polymers are hydrophobic (hence showing poor cell attachment) with limited bioactivity and functional groups for post-tethering of growth factors and proteins [78]. Electrospun natural polymers, which include collagen [79], gelatin [80], silk fibrin [81, 82] and chitosan [83], have the key advantages of exhibiting enhanced biofunctional motifs, are much more hydrophilic and in turn support superior cell adhesion [78]. Initial cell adhesion and survival is eminent in the consequential success and effectiveness of the bone graft. However, natural polymers have greater structural, chemical and molecular weight variability and a higher possibility of immune rejection. Furthermore, there is much less versatility in regards to electrospinning control and ease, in that only few solvents do not denature natural polymers, narrowing the window of solution and operating conditions to permit electrospinnability.

There has been substantial investigation into combining the properties of both natural and synthetic polymers via electrospinning various polymer blends such as PCL with Hep-S [84], gelatin [85] and silk fibrin [78, 86]. The benefits of co-incorporating natural and synthetic polymers have been demonstrated in a comparative study by Lee et al. [87], highlighting that the addition of collagen into PCL significantly increases hydrophilicity, degradation rate, mechanical elongation, cell adhesion and growth *in vitro*, cellular infiltration *in vivo*, and up-regulation of OP, ALP activity and collagen type I in osteoprogenitor cells. Furthermore, the blending of SIS with PCL in an layered micro/nano dual fiber size construct provided

approximately a fourfold increase in proliferation of BMSCs, possibly linked to an increase in hydrophilicity and thus cell adhesion [86]. Importantly, incorporation of layers of electrospun fibers without SIS had no significant impact on the cellular response. Blending PCL with Hep-S [84], a carrier for human MSCs, improved the *in vitro* growth of these osteoprogenitor cells. Heparin alone showed some improvement, but only half that of Hep-S. Indeed Hep-S has the intrinsic ability to regulate numerous functional growth factors involved in post-fracture bone [88]. When implanted, there was no protective carrier for the cells, so any impact of the Hep-S on bone formation could not be accurately evaluate given the likely intervention of host inflammatory responses [84].

6.3.1.2 Inorganic Nanofibers

A novel approach to overcoming the polymer nanofibers shortcomings (which include limited integration with the host tissue and insufficient mechanical properties) is to electrospin inorganic (ceramic) nanofibers, shown in Fig. 6.1. While the material processing of such nanofibers has been well reported [89], their involvement in the bio-industry has been relatively untapped, in particular their effects on cellular responses *in vitro* and *in vivo*. Inorganic electrospun fibers have predominately been obtained via electrospinning sol-gels of polymer and ceramic components, followed by heat treatment up to 700 °C [90] to burn the binding polymer off, thus leaving ceramic fibers. Nanofibrous matrices of silicate [91], bioactive glass [90, 92, 93], FAp [94] and HAp [95] are potential integrative materials for bone tissue regeneration. Bioactive glass has intrinsic anti-inflammatory and anti-microbial capabilities [96], the capacity to up-regulate the secretion of growth factors [97], and can stimulate mineralisation [92]. Cell viability and ALP activity of bone-marrow-derived human MSCs on bioactive glass nanofibers significantly superseded that of bioactive glass discs and PCL nanofiber controls [90]. Despite superior bioactivity and dramatic increases in modulus and mechanical strength, inorganic nanofibers have the limitations of being too brittle as bone-graft candidates [95, 98].

6.3.1.3 Composite Nanofibers

The hybrid material properties obtained via biodegradable polymers and bioactive particles within electrospun nanocomposites are intuitively more suitable for functional bone substitutes. Pre-blending HAp nanoplates [99, 100], carbon nanotubes [101], bioactive glass [102] and various calcium phosphates within electrospun biodegradable polymers has been a logical, exciting and successful approach for promoting cell anchorage and bone-specific bioactivity with improvements in fiber mechanical properties, nano-roughness and hydrophilicity. Advances in osteoconductivity (the recruitment and stimulated in-growth of osteoprogenitor cells and neo-blood vessels from the host tissue into the scaffold [59, 103]) and osteoinductivity (the capacity to induce bone formation directly [59, 103]) have been achieved with the integrated complexity of such a composite system.

Fig. 6.1 Electrospun polymer, inorganic and composite fibers. (a) SEM image of electrospun P_LLA (860 ± 110 nm) (adapted with permission from [100]). (b) TEM image of electrospun PVA/collagen nanofibers (~ 245 nm) (adapted with permission from [104]). (c) SEM image of aligned HAp nanofibers post-removal of poly(vinyl pyrrolidone) via heat treatment at 600°C for 6 h. (d) High magnification SEM image of HAp nanofibers displaying fusing of adjacent HAp nanorods (diameter of ~ 7 nm and length of ~ 27 nm); (Both (c) and (d) adapted with permission from [95]). (e) SEM image of blended P_LLA/HAp (wt ratio 4:1) electrospun composite fibers: 845 ± 140 nm (adapted with permission from [100]) (f) TEM image of composite PVA/collagen/HAp nanorod blended nanofibers (~ 320 nm) (adapted with permission from [104])

Apatite/Polymer Composite Fibers

Biomimetic electrospun structures consisting of nano-HAp with various biodegradable polymers have been well explored [99, 104] (refer to Fig. 6.1). The effectiveness of nanoparticulate, reinforced polymeric matrices is critically dependent on the dispersion uniformity and binding affinity at the polymer-particle interface. Surfactant adsorption of hydroxyteric acid [105] and Hep [106], grafting of PCL [107], electrostatic dispersion via pH changes [108] and HAp silica coating [109] feature as some of the possible techniques to reduce the inherent tendency for nano-HAp particles to aggregate, thereby improving their interaction with the matrix.

Recently, more sophisticated additions including incorporation of chemical variations of apatite have shown potent effects in stimulating the cellular response. TCP [110] and carbonated-apatite [111] dissolve faster than nano-HAp and are more readily taken up by osteoclasts, whereby an initially rich calcium and phosphorous microenvironment facilitates more rapid bone redevelopment. Stable bone-specific inorganics, such as FAp [94], sustain slower calcium dissolution rates, where combining it with HAp (40% FAp:60% HAp) enhanced osteoblastic cell survival and expression of OPG, OC and BSP-1 in vitro on flame-sprayed orthopaedic coatings [112]. Similarly, Arinze et al. reported a combination of HAp with β -TCP (20:80) promoted far higher MSC bone deposition than each individual component in vitro and in vivo [113]. Intuitively, a combination of inorganic crystals that can lead to rapid osteoconductivity and osteoinductivity for primary fixation stability and integration with the host tissue, while maintaining osteogenesis until the defect has healed, are best suited. However, dissolution is only one parameter that determines the choice of inorganic bioactive ceramics; structural integrity during degradation, biocompatibility, particle size, shape, crystallinity, surface chemistry, and binding and dispersive interaction with the polymer co-component are all vital for controlling the endogenous response.

The necessity to provide a combination of bio-stimulative phases has been supported by statistically higher cell number and ALP activity of adult human BMSCs on combinations of HAp (50:50) with two different bioactive glasses than on each bioactive glass and HAp nano-rough ceramic surface alone [114]. The combinatorial benefits of HAp with bioactive glass has also recently been applied to Ti-orthopaedic implants and shown to supersede the initial cell adhesion, proliferation and sustained osteogenic differentiation of commercially available HAp coatings [96].

Carbon Nanotubes in Electrospun Fibers

As a result of their highly specialised combination of aspect ratio (surface area), strength, stiffness, light weight and versatile surface chemical functionalisation [115], the incorporation of carbon nanotubes within electrospun polymers has provided a unique platform for bone tissue engineering. Dramatic increases in stiffness, strength and elongation have also been reported [116]. The addition of 0.02 wt% MWCNTs into silk fibrin nanofibers increased the modulus from 231.2 ± 13.7 MPa to 342.7 ± 16.2 MPa; tensile strength 6.7 ± 0.7 MPa to 10.0 ± 1.0 MPa, but elongation decreased from 16.8% to 11.7% [117]. However, the properties were dependent on dispersion, functionalisation and nanotube concentrations. Reduction in mechanical properties, slower biodegradation rate and increases in fiber diameter were observed with increases in non-functionalised MWCNT concentration beyond 0.5 wt% [116]. Similar to blending apatite nano-crystals, surface functionalisation has been critical for dispersion to enable the significant addition of nanotubes without aggregation and decline in material properties. These properties will also improve adhesion with the polymeric matrix [118] and biocompatibility [119]. PCL has been grafted onto MWNTs to create a hard-core/soft-shell structure, again targeted for "artificial bones" [120]. However, the addition of carbon nanotubes into electrospun fibers has had varied effects on scaffold mechanical properties. While covalently-functionalised carbon nanotubes may provide better dispersion throughout the fiber, their effect can be mechanically detrimental. Functional groups in the graphene lattice also act as defect points that can weaken the nanotube and corresponding electrospun fiber [121].

Biologically, the presence of nanotubes has also enhanced bone-specific bioactivity: fibrous blends of biocompatible MWCNTs and PLGA (2.15 μ m), stimulate apatite mineralisation from SBF without the presence of any cells [101]. Furthermore, co-blending of both HAp nanoparticles and MWNTs within PLGA [122] has been proposed as attractive nanocomposites for bone tissue engineering, exhibiting both attachment and proliferation of bone-marrow-delivered MSCs.

Core-Shell Electrospinning

Despite the advantages in pre-blending particles with biodegradable polymers to yield electrospun nanocomposite fibers, the spatial organisation within the fiber is

still random. As a result, it is not yet possible to mimic the physical and chemical organisation of mineralised fibrils in native bone. However, improvements may be realised through core-shell electrospinning (also referred to as co-axial electrospinning). This is conceptually similar to single jet electrospinning, however, it involves a dual-orifice spinneret whereby two separate solutions are simultaneously fed through an outer and inner needle to create dual-layered nanofibers [123, 124].

One of the crucial advantages in core-shell electrospinning is that there are fewer restrictions on the solution properties, with the shell acting as a guide to form appropriately layered structures [124]. While not yet extensively explored, core solutions including low-molecular weight polymers, molecules with limited solubility, metallic and ceramic particles [124] and even cells (which have been demonstrated to maintain full functionality post-electrospinning) [125] are potential candidates for unique advances in bone tissue engineering.

6.3.2 *Dual Porosity, Cellular Infiltration and Three-Dimensional Structures*

Scaffold three-dimensionality with interconnected microporosity for cellular infiltration, vascularisation and integration with the patient's tissue is paramount for the clinical viability of the adjuvant synthetic matrix. Host tissue in-growth and consequential mechanical interlocking is of key importance for effective osseointegration and implant stability. Not only does the stability of the implant influence healing time, pain and physical support, the micromechanics imposed in the endogenous niche have a critical influence over the formation of neo-blood vessels, osteoprogenitor differentiation, proliferation, migration, inflammatory response [59, 126], and ultimately the quantity and quality of newly formed bone. This is one of the major inherent limitations with electrospun matrices: the pores are too small.

The increasingly prevalent need to provide micropores while maintaining nanomimetic features and porosity for which cell nutrients and metabolic waste are transported [127] has lead to combining a range of fabrication technologies with electrospinning. Dual-scale porosity in electrospun nanofiber matrices has been improved through co-incorporating electrospun water-soluble sacrificial fibers [128–130], ice crystals [131–133], micron-sized fibers produced by heated melt deposition [76, 86, 134] or co-electrospinning [135], salt leaching [136, 137], salt leaching/gas foaming techniques [127, 138], drawing a metallic comb through the fibers to expand the mesh mechanically [139], using a metallic spherical dish as a collector of the electrospun fibers [140] and cutting pores out using laser ablation [141], some of which are shown in Fig. 6.2.

While many of these approaches increase cellular infiltration and/or survival, a major pitfall that accompanies increased porosity is the subsequent reduction in mechanical strength. In an attempt to overcome this issue, Lee et al. [127] co-blended MMT nano-sized platelets as reinforcements in electrospun P_LLA and used salt leaching/gas foaming to create a reinforced three-dimensional nanofibrous mesh

Fig. 6.2 Methods for generating microporosity within electrospun nanofibrous scaffolds. (a) Schematic simultaneous electrospinning of PLLA with PEO onto a common rotating drum (concepts derived from [130]). (b) SEM image of electrospun PLLA/PEO (1:3), post-removal of PEO and fiber mineralisation in SBF (adapted with permission from [130]). (c) Electrospun PCL collected in an electrically grounded reservoir of water. Nanofibers drained into a lower reservoir where the vortex fluid motion confined PCL fibers into yarned bundles that were collected in reservoir 2. Slurry of PCL fibrous yarns and water from reservoir 2 was moulded into cylindrical three-dimensional structures, immersed in liquid nitrogen (-196°C) for 15 min and freeze dried; (d) corresponding SEM image; ((c) and (d) adapted with permission from [133]). (e) Simultaneous deposition of salt particles (100–200 μm) during electrospinning of collagen/sodium hyaluronate

with micro-sized pores. Opportunistic bone-specific strengthening systems as discussed in sect. 6.3.1.3 may be important in combination with dual-scale porous scaffolds to create fully functional three-dimensional bone-graft implants.

Open microporosity may also be crucial in effective tissue regeneration, yet without active surface chemistry as discussed below, host infiltration is likely to be ineffective. It has been suggested that modified surface chemistry on its own can encourage tissue infiltration, and is likely to be a prerequisite. This has been supported through *in vitro* and *in vivo* studies of Hep-coated P_LLA nanofibers, where in-growth of bovine aortic endothelial cells into three-dimensional scaffolds was improved with Hep coating, and interestingly through using aligned fibers [142]. More potently, as neural cell migration can be driven by neurotrophin-2 and nerve growth factor gradients [143], there may be potential for encouraging bone-specific infiltration via bone-specific gradients.

6.3.3 Surface Functionalisation

The ability to modify the surface chemistry on the nanofibers facilitates manipulation and tuning of biological responses for bone regeneration. Greater surface exposure of bone-specific inorganics, cell adhesive molecules and growth factors attachment has been achieved through various novel surface modification techniques discussed below. The ability to expose multiple drugs and growth factors from electrospun systems is an exciting prospect for sophisticated bio-regenerative signalling, yet currently in its developmental infancy.

6.3.3.1 Surface Activation Techniques and Hydrophilicity

An alternative technique for increasing cell affinity and biocompatibility of synthetic electrospun polymers involves modification of the surface of electrospun fibers via the attachment of hydrophilic chemical groups such as amides, carboxyl and hydroxyl groups [144]. *In situ* grafting of hydrophilic acrylic acid on to PGA, P_LLA and PLGA electrospun fibers for increased presentation of carboxyl groups facilitated significant improvements in fibroblast attachment, spreading and proliferation *in vitro* [145]. Importantly, these reactive groups are prerequisites for providing docking sites for adsorption and/or the immobilisation of an extensive range of growth factors, proteins and peptides. Often spacer molecules are also attached onto the fiber via polymerisation grafting, to change the surface biochemistry and provide docking sites for immobilisation of more powerful biological molecules and to maintain bioactivity [144].

←
Fig. 6.2 (continued) (80/20); **(f)** High magnification SEM image of dried scaffold post-collagen/sodium hyaluronate cross-linking and salt leaching; **((e) and (f))** adapted with permission from [136]. **(g)** Schematic stacking of PCL/collagen type I blended electrospun nanofibers with microfibers via direct polymer melt deposition; **(h)** SEM image of electrospun nanofibers on top of microfibers; **((g) and (h))** adapted with permission from [76]

6.3.3.2 Macromolecules, Natural Polymers and Signalling Factors Involved in Bone Healing

Following surface pre-activation, collagen [146], gelatin [147] and fibronectin [29] have been tethered onto electrospun synthetic polymers to increase bio-functionality. Cell adhesive ligands, including RGD-containing peptides, have also been attached to electrospun synthetic biodegradable polymers, leading to enhanced control over attachment, spreading [148], proliferation and differentiation of a variety of osteoprogenitor stem cells [149, 150]. Owing to its high negative charge, Hep attachment onto electrospun fibers has been important for electrostatic adsorption of a variety of growth factors involved in bone morphogenesis, such as FGF-2 [151], VEGF, TGF- β [152] and PDGF [153]. Furthermore, dual-immobilisation of laminin and FGF onto Hep functionalised P₄LA nanofibers showed enhanced bioactivity [154]. Conversely, Hep has been shown to suppress BMP-2 osteogenic bioactivity [155] and thus control over Hep location, concentration and timed exposure should therefore be taken into careful consideration in designing multiple growth factor delivery systems for bone tissue engineering.

Not only does the selection of bio-signalling molecules have a great influence over regulating cellular response, the immobilisation mechanism is crucial. The two major surface attachment techniques include covalent conjugation and adsorption via secondary forces. Typically, conjugation has been linked with sustained signal exposure yet greater chances of protein bio-deactivation, while adsorption only supports burst delivery. Importantly, a comparison between these two techniques has been shown for attachment of BMP-2 [156]. BMPs can stimulate osteoblastic differentiation of MSCs in vitro [157], initiate bone osteoinduction and osteoconduction in endochondral and intramembranous regenerative cascades [158], and even play a concurrent role in mediating angiogenesis [159]. Conjugation of BMP-2 onto cast PCL films showed greater concentrations of BMP attached with a slower accumulated release, in contrast to adsorption of BMP [156]. Greater ALP and OC expression from BMSCs (15 days in culture) was observed with covalent attachment of BMP-2, suggesting that this conjugation maybe a more favourable attachment mechanism [156].

6.3.3.3 Calcium Phosphate Coatings

One convenient technique utilised in developing bone-specificity on electrospun fibers has been coating biodegradable fibers with HAp and various calcium phosphates via immersion in SBF [160]. Surface presentation of selective chemical groups on biodegradable fibers is a prerequisite for stimulating surface nucleation and growth of HAp when incubated in calcium- and phosphate-rich SBF solutions [161]. Various techniques have been used to create surface active groups which can support the nucleation of calcium phosphate phase, some of which include plasma treatment [145, 162], alkaline erosion [163] and LbL coating [164]. An elegant study by Cui

et al. utilised covalent grafting of chitosan on amino-functionalised P_{DL} LA fibers to facilitate controlled HAp deposition with uniform surface coverage. The presence of chitosan and mineralisation showed improved proliferation and differentiation of osteoprogenitor cells in comparison to controls [165]. However, a distinct disadvantage in surface deposition of HAp, rather than blending within the fiber, is that there is virtually no improvement in mechanical properties.

6.3.3.4 Electrospin/Electrospray Systems

Utilisation of electrospraying has been recently proposed as an alternative technique to enable strategic engineering control over the spatial organisation of each constituent phase in electrospun nanocomposites [166, 167]. Francis et al. [168] recently utilised simultaneously electrospraying of HAp and electrospinning of gelatin fibers onto a common rotating drum collector. Gelatin fibers were cross-linked, which increased the mechanical strength and elongation. As HAp particles were electrosprayed onto the surface of the gelatin fibers, this resulted in greater HAp exposure and enhanced surface "nano-roughness," alleviating problems such as the loss of HAp platelet bioactivity that may result if blended within the fiber. This spin-spray system provided appreciable enhancement in human foetal osteoblast proliferation, mineralisation and ALP after 15 days of culture, in comparison to blended gelatin/HAp electrospun fibers [168].

Spraying technologies also offer potentially more effective incorporation of mechanically mismatched materials, which may otherwise be detrimental if physically mixed together. However, despite various improvements in mechanical properties, material technologies are yet to be able to produce electrospun bioactive composites that can be utilised as stand-alone, temporary bone substitutes.

6.3.3.5 Layer-by-Layer Surface Modification of Nanofibers

Alternate electrostatic assembly of anionic and cationic electrolyte layers is a highly attractive means of altering nanofiber surface chemistry and coating a nano-thin biological reservoir of growth factors, drugs and proteins onto the electrospun fibers. Within the cellular environment, growth factors are released by degradation of inter-layer bonding as a result of aqueous, enzymatic or cellular activity. A wide variety of lipid vesicles, nucleic acids, DNA, proteins and more recently growth factors have been immobilised in LbL coatings with broad biological benefits [169–171]. Higher concentrations of molecules can be accumulated in a robust and controlled manner by simply increasing the number of assembled layers [144, 170]. Loading efficiency currently limits the clinical application of many growth factors such as rhBMP-2 [172]. Encapsulation of rhBMP-2 in cross-linked poly-L-lysine/hyaluronan LbL films, which could be coated onto nickel-titanium implant surfaces, maintained near zero-order release kinetics and protein bioactivity over 10 days, and promoted *in vitro* differentiation of myoblasts into osteoblasts [173]. A variety of bonding

forces, beyond the most common electrostatic interactions, including hydrogen bonding, hydrophobic interaction and covalent bonding, can also be used to control the biomolecular retention and release kinetics [174].

6.3.4 Cellular-Based Matrices

The design of artificial microenvironments for repair needs to accommodate the specific cell types and their interface with region-specific physical and pharmacological parameters. With bone, these should be specific to those activated during endogenous regeneration. As cells ultimately define the repair process, their involvement with the scaffold is an eminent step in therapeutic tissue engineering.

Various cell-encapsulating devices have been implemented to increase delivery efficiency, longer-term viability and function as opposed to direct cellular re-injection. MSCs can proliferate and differentiate on two-dimensional culture surfaces with the addition of growth factors, proteins, cytokines and hormones active in the bone healing cascade along with various anti-inflammatories and antimicrobials added into the culture medium [175]. Once dense differentiated populations of MSCs are achieved, they can be seeded on three-dimensional electrospun scaffolds as discussed throughout this review and correspondingly implanted. Alternatively, proliferation could be encouraged directly on the scaffolds in vitro. There have been few innovative approaches to cell-encapsulation within electrospun scaffolds. Recently, this has begun to change with research involving electrospraying of cells [176], encapsulating cells inside individual electrospun fibers [125, 177] and three-dimensional stacking of cells between electrospun layers [178].

6.4 Summary and Future Perspectives

There is an ever-increasing need to improve the clinical management of skeletal disorders. While not necessarily life threatening, these conditions severely impact quality of life and present a major economic burden on society. Recently, the process of bone repair has received great impetus from progress made in engineering (nanotechnology) and biomedicine (bone stem and progenitor cells). Innovative strategies to combine each field have provided a rational and strategic framework to transform the clinical management of skeletal disease repair.

Establishing a nano-framework using natural and synthetic polymers, in combination with apatite crystals, functionalised nanotubes and/or bioactive glass underpins the mechanical properties of scaffolds that are critical for functional bone development. It is envisaged that combining techniques will yield more biomimetic and structurally sound synthetic ECM. Importantly, improved design of smart biomatrices that target bone regeneration is of great importance. Surface engineering via adsorption immobilisation, covalent conjugation and LbL coatings provide unique platforms

for releasing/presenting growth factors that stimulate bone regeneration from electrospun scaffolds. It is visioned that cooperative interaction of tissue engineering at multiple levels of matrix sophistication with stem cell-based therapies will ultimately expedite bone healing. The challenge is how they can be strategically combined.

References

1. Vallet-Regí M, Arcos D (2008) Nanostructured hybrid materials for bone implants fabrication. In: Ruiz-Hitzky E, Ariga K, Lvov YM (eds) *Bio-inorganic hybrid nanomaterials: strategies, syntheses, characterization and applications*. Wiley, Weinheim, Germany
2. Balasundaram G (2007) Nanomaterials for better orthopedics. In: Webster TJ (ed) *Nanotechnology for the regeneration of hard and soft tissues*. World Scientific Publishing, Singapore
3. Tiegs RD (1997) Paget's disease of bone: Indications for treatment and goals of therapy. *Clin Ther* 19(6):1309–1329
4. Reginster J, Burlet N (2006) Osteoporosis: a still increasing prevalence. *Bone* 38(2):4–9
5. Assouline-Dayana Y, Chang C, Greenspan A et al (2002) Pathogenesis and natural history of osteonecrosis. *Semin Arthritis Rheum* 32(2):94–124
6. Simon LS (1999) Osteoarthritis: a review. *Clin Cornerstone* 2(2):26–37
7. Reddy SV, Kurihara N, Menaa C et al (2001) Paget's disease of bone: a disease of the osteoclast. *Rev Endocr Metab Disord* 2(2):195–205
8. Glorieux F (2008) Osteogenesis imperfecta. *Best Pract Res Clin Rheumatol* 22(1):85–100
9. Lindsay R, Christiansen C, Einhorn TA et al (1997) Who are candidates for prevention and treatment for osteoporosis? *Osteoporos Int* 7(1):1–6
10. Gullberg B, Johnell O, Kanis JA (1997) World-wide projections for hip fracture. *Osteoporos Int* 7(5):407–413
11. Giannoudis PV, Dinopoulos H, Tsiridis E (2005) Bone substitutes: an update. *Injury* 36(Suppl 3):20–27
12. Beutner R, Michael J, Schwenzer B et al (2009) Biological nano-functionalization of titanium-based biomaterial surfaces: a flexible toolbox. *J R Soc Interface* 7(Suppl 1):S93–S105
13. Johnsen SP, Sørensen HT, Pedersen AB et al (2006) Patient-related predictors of implant failure after primary total hip replacement in the initial, short- and long-terms: a nationwide Danish follow-up study including 36 984 patients. *J Bone Joint Surg Ser B* 88(10):1303–1308
14. De Long WG Jr, Einhorn TA, Koval K et al (2007) Bone grafts and bone graft substitutes in orthopaedic trauma surgery: a critical analysis. *J Bone Joint Surg Ser A* 89(3):649–658
15. Finkemeier CG (2002) Bone-grafting and bone-graft substitutes. *J Bone Joint Surg Ser A* 84(3):454–464
16. Rogel MR, Qiu H, Ameer GA (2008) The role of nanocomposites in bone regeneration. *J Mater Chem* 18(36):4233–4241
17. Liu X, Chu P, Ding C (2004) Surface modification of titanium, titanium alloys, and related materials for biomedical applications. *Mat Sci Eng R Rep* 47(3–4):49–121
18. Li D, Xia Y (2004) Electrospinning of nanofibers: reinventing the wheel? *Adv Mater* 16(14):1151–1170
19. Reneker DH, Yarin AL (2008) Electrospinning jets and polymer nanofibers. *Polymer* 49(10):2387–2425
20. Hohman MM, Shin M, Rutledge G et al (2001) Electrospinning and electrically forced jets. II. Applications. *Phys Fluids* 13(8):2221–2236
21. Hohman MM, Shin M, Rutledge G et al (2001) Electrospinning and electrically forced jets. I. Stability theory. *Phys Fluids* 13(8):2201

22. Salgado AJ, Coutinho OP, Reis RL (2004) Bone tissue engineering: state of the art and future trends. *Macromol Biosci* 4(8):743–765
23. Gaalen Sv, Kruyt M, Meijer G et al (2008) Tissue engineering of bone. In: Blitterswijk CV, Thomsen P, Lindahl A et al (eds) *Tissue engineering*. Elsevier, London
24. Barrère F, van Blitterswijk CA, de Groot K (2006) Bone regeneration: molecular and cellular interactions with calcium phosphate ceramics. *Int J Nanomedicine* 1(3):317–332
25. Lui H, Webster TJ (2007) Bioinspired nanocomposites for orthopedic applications. In: Webster TJ (ed) *Nanotechnology for the regeneration of hard and soft tissues*. World Scientific Publishing, Singapore
26. Rho JY, Kuhn-Spearing L, Zioupos P (1998) Mechanical properties and the hierarchical structure of bone. *Med Eng Phys* 20(2):92–102
27. Espinosa HD, Rim JE, Barthelat F et al (2009) Merger of structure and material in nacre and bone – perspectives on *de novo* biomimetic materials. *Prog Mat Sci* 54(8):1059–1100
28. Weiner S, Wagner HD (1998) The material bone: structure-mechanical function relations. *Annu Rev Mater Sci* 28(1):271–298
29. Jang JH, Castano O, Kim HW (2009) Electrospun materials as potential platforms for bone tissue engineering. *Adv Drug Deliv Rev* 61(12):1065–1083
30. Gupta HS, Seto J, Wagermaier W et al (2006) Cooperative deformation of mineral and collagen in bone at the nanoscale. *Proc Natl Acad Sci USA* 103(47):17741–17746
31. Fratzl P, Gupta HS, Paschalis EP et al (2004) Structure and mechanical quality of the collagen-mineral nano-composite in bone. *J Mater Chem* 14(14):2115–2123
32. Sommerfeldt D, Rubin C (2001) Biology of bone and how it orchestrates the form and function of the skeleton. *Eur Spine J* 10(Suppl 2):S86–S95
33. Knott L, Bailey AJ (1998) Collagen cross-links in mineralizing tissues: a review of their chemistry, function, and clinical relevance. *Bone* 22(3):181–187
34. Launey ME, Buehler MJ, Ritchie RO (2010) On the mechanistic origins of toughness in bone. *Annu Rev Mater Res* 40(1):25–53
35. Kadler KE, Holmes DF, Trotter JA et al (1996) Collagen fibril formation. *Biochem J* 316(1):1–11
36. Hassenkam T, Fantner G, Cutroni J et al (2004) High-resolution AFM imaging of intact and fractured trabecular bone. *Bone* 35(1):4–10
37. Landis WJ, Hodgins KJ, Song MJ et al (1996) Mineralization of collagen may occur on fibril surfaces: evidence from conventional and high-voltage electron microscopy and three-dimensional imaging. *J Struct Biol* 117(1):24–35
38. Kadler KE, Hill A, Canty-Laird EG (2008) Collagen fibrillogenesis: fibronectin, integrins, and minor collagens as organizers and nucleators. *Curr Opin Cell Biol* 20(5):495–501
39. Wenstrup RJ, Florer JB, Brunskill EW et al (2004) Type v collagen controls the initiation of collagen fibril assembly. *J Biol Chem* 279(51):53331–53337
40. Alford AI, Hankenson KD (2006) Matricellular proteins: extracellular modulators of bone development, remodeling, and regeneration. *Bone* 38(6):749–757
41. Giachelli CM, Steitz S (2000) Osteopontin: a versatile regulator of inflammation and biomineralization. *Matrix Biol* 19(7):615–622
42. Hoang QQ, Sicheri F, Howard AJ et al (2003) Bone recognition mechanism of porcine osteocalcin from crystal structure. *Nature* 425(6961):977–980
43. Bradshaw AD, Sage EH (2001) Sparc, a matricellular protein that functions in cellular differentiation and tissue response to injury. *J Clin Invest* 107(9):1049–1054
44. Shekaran A, García AJ (2011) Extracellular matrix-mimetic adhesive biomaterials for bone repair. *J Biomed Mater Res A* 96A(1):261–272
45. Bellahcène A, Bonjean K, Fohr B et al (2000) Bone sialoprotein mediates human endothelial cell attachment and migration and promotes angiogenesis. *Circ Res* 86(8):885–891
46. Bornstein P (2001) Thrombospondins as matricellular modulators of cell function. *J Clin Invest* 107(8):929–934
47. Midwood K (2004) Tissue repair and the dynamics of the extracellular matrix. *Int J Biochem Cell Biol* 36(6):1031–1037

48. Taylor DK, Meganck JA, Terkhorn S et al (2009) Thrombospondin-2 influences the proportion of cartilage and bone during fracture healing. *J Bone Miner Res* 24(6):1043–1054
49. Vaananen H, Laitalaheinonen T (2008) Osteoclast lineage and function. *Arch Biochem Biophys* 473(2):132–138
50. Teitelbaum SL, Ross FP (2003) Genetic regulation of osteoclast development and function. *Nat Rev Genet* 4(8):638–649
51. Heino TJ, Hentunen TA (2008) Differentiation of osteoblasts and osteocytes from mesenchymal stem cells. *Curr Stem Cell Res Ther* 3(2):131–145
52. Kartsogiannis V, Ng K (2004) Cell lines and primary cell cultures in the study of bone cell biology. *Mol Cell Endocrinol* 228(1–2):79–102
53. Huang C, Ogawa R (2010) Mechanotransduction in bone repair and regeneration. *J Fed Am Soc Exp Biol* 24:p3625–p3632
54. You J, Yellowley CE, Donahue HJ et al (2000) Substrate deformation levels associated with routine physical activity are less stimulatory to bone cells relative to loading-induced oscillatory fluid flow. *J Biomech Eng* 122(4):387–393
55. Boyce B, Xing L (2008) Functions of RANKL/RANK/OPG in bone modeling and remodeling. *Arch Biochem Biophys* 473(2):139–146
56. Schindeler A, McDonald M, Bokko P et al (2008) Bone remodeling during fracture repair: the cellular picture. *Semin Cell Dev Biol* 19(5):459–466
57. Gerstenfeld LC, Cullinane DM, Barnes GL et al (2003) Fracture healing as a post-natal developmental process: molecular, spatial, and temporal aspects of its regulation. *J Cell Biochem* 88(5):873–884
58. Carano RAD, Filvaroff EH (2003) Angiogenesis and bone repair. *Drug Discov Today* 8(21):980–989
59. Willie BM, Petersen A, Schmidt-Bleek K et al (2010) Designing biomimetic scaffolds for bone regeneration: why aim for a copy of mature tissue properties if nature uses a different approach? *Soft Matter* 6(20):4976–4987
60. Ferguson C, Alpern E, Miclau T et al (1999) Does adult fracture repair recapitulate embryonic skeletal formation? *Mech Dev* 87(1–2):57–66
61. Shapiro F (2008) Bone development and its relation to fracture repair. The role of mesenchymal osteoblasts and surface osteoblasts. *Eur Cell Mater* 15:53–76
62. Ai-Aql ZS, Alagl AS, Graves DT et al (2008) Molecular mechanisms controlling bone formation during fracture healing and distraction osteogenesis. *J Dent Res* 87(2):107–118
63. Phillips A (2005) Overview of the fracture healing cascade. *Injury* 36(3):S5–S7
64. Dimitriou R, Tsiridis E, Giannoudis P (2005) Current concepts of molecular aspects of bone healing. *Injury* 36(12):1392–1404
65. Yoshimoto H (2003) A biodegradable nanofiber scaffold by electrospinning and its potential for bone tissue engineering. *Biomaterials* 24(12):2077–2082
66. Sisson K, Zhang C, Farach-Carson MC et al (2010) Fiber diameters control osteoblastic cell migration and differentiation in electrospun gelatin. *J Biomed Mater Res A* 94A(4):1312–1320
67. Bondar B, Fuchs S, Motta A et al (2008) Functionality of endothelial cells on silk fibroin nets: comparative study of micro- and nanometric fiber size. *Biomaterials* 29(5):561–572
68. Badami AS, Kreke MR, Thompson MS et al (2006) Effect of fiber diameter on spreading, proliferation, and differentiation of osteoblastic cells on electrospun poly(lactic acid) substrates. *Biomaterials* 27(4):596–606
69. Chen M, Patra PK, Lovett ML et al (2009) Role of electrospun fiber diameter and corresponding specific surface area (SSA) on cell attachment. *J Tissue Eng Regen Med* 3(4):269–279
70. Del Gaudio C, Bianco A, Folini M et al (2009) Structural characterization and cell response evaluation of electrospun PCL membranes: micrometric versus submicrometric fibers. *J Biomed Mater Res A* 89A(4):1028–1039
71. Chen M, Patra PK, Warner SB et al (2007) Role of fiber diameter in adhesion and proliferation of NIH 3 T3 fibroblast on electrospun polycaprolactone scaffolds. *Tissue Eng* 13(3):579–587

72. Szentivanyi A, Chakradeo T, Zernetsch H et al (2010) Electrospun cellular microenvironments: understanding controlled release and scaffold structure. *Adv Drug Deliv Rev* 63(4–5): 209–220
73. Pham QP, Sharma U, Mikos AG (2006) Electrospun poly (ϵ -caprolactone) microfiber and multilayer nanofiber/microfiber scaffolds: characterization of scaffolds and measurement of cellular infiltration. *Biomacromolecules* 7(10):2796–2805
74. Huebsch N, Arany PR, Mao AS et al (2010) Harnessing traction-mediated manipulation of the cell/matrix interface to control stem-cell fate. *Nat Mater* 9(6):518–526
75. Heo S-J, Kim S-E, Wei J et al (2008) Fabrication and characterization of novel nano- and micro-HA/PCL composite scaffolds using a modified rapid prototyping process. *J Biomed Mater Res A* 89A(1):108–116
76. Park SH, Kim TG, Kim HC et al (2008) Development of dual scale scaffolds via direct polymer melt deposition and electrospinning for applications in tissue regeneration. *Acta Biomater* 4(5):1198–1207
77. Sung H (2004) The effect of scaffold degradation rate on three-dimensional cell growth and angiogenesis. *Biomaterials* 25(26):5735–5742
78. Lee H, Kim G (2010) Biocomposites electrospun with poly(ϵ -caprolactone) and silk fibroin powder for biomedical applications. *J Biomater Sci Polym Ed* 21(13):1687–1699
79. Chan CK, Liao S, Li B et al (2009) Early adhesive behavior of bone-marrow-derived mesenchymal stem cells on collagen electrospun fibers. *Biomed Mater* 4(3):035006
80. Zhao J, Zhao Y, Guan Q et al (2011) Crosslinking of electrospun fibrous gelatin scaffolds for apatite mineralization. *J Appl Poly Sci* 119(2):786–793
81. Park SY, Ki CS, Park YH et al (2010) Electrospun silk fibroin scaffolds with macropores for bone regeneration: an in vitro and in vivo study. *Tissue Eng Part A* 16(4):1271–1279
82. Meechaisue C, Wutticharoenmongkol P, Waraput R et al (2007) Preparation of electrospun silk fibroin fiber mats as bone scaffolds: a preliminary study. *Biomed Mater* 2(3): 181–188
83. Geng X, Kwon O, Jang J (2005) Electrospinning of chitosan dissolved in concentrated acetic acid solution. *Biomaterials* 26(27):5427–5432
84. Luong-Van E, Grøndahl L, Song S et al (2007) The in vivo assessment of a novel scaffold containing heparan sulfate for tissue engineering with human mesenchymal stem cells. *J Mol Histol* 38(5):459–468
85. Kim H-W, Yu H-S, Lee H-H (2008) Nanofibrous matrices of poly(lactic acid) and gelatin polymeric blends for the improvement of cellular responses. *J Biomed Mater Res A* 87A(1):25–32
86. Yoon H, Ahn S, Kim G (2009) Three-dimensional polycaprolactone hierarchical scaffolds supplemented with natural biomaterials to enhance mesenchymal stem cell proliferation. *Macromol Rapid Commun* 30(19):1632–1637
87. Lee J-J, Yu H-S, Hong S-J et al (2009) Nanofibrous membrane of collagen–polycaprolactone for cell growth and tissue regeneration. *J Mater Sci Mater Med* 20(9):1927–1935
88. Jackson RA, McDonald MM, Nurcombe V et al (2006) The use of heparan sulfate to augment fracture repair in a rat fracture model. *J Orthop Res* 24(4):636–644
89. Chronakis I (2005) Novel nanocomposites and nanoceramics based on polymer nanofibers using electrospinning process – a review. *J Mater Process Technol* 167(2–3):283–293
90. Kim HW, Kim HE, Knowles JC (2006) Production and potential of bioactive glass nanofibers as a next-generation biomaterial. *Adv Func Mater* 16(12):1529–1535
91. Sakai S, Yamada Y, Yamaguchi T et al (2006) Prospective use of electrospun ultra-fine silicate fibers for bone tissue engineering. *Biotechnol J* 1(9):958–962
92. Xia W, Zhang D, Chang J (2007) Fabrication and in vitro biomineralization of bioactive glass (BG) nanofibers. *Nanotechnology* 18(13):135601
93. Lu H, Zhang T, Wang XP et al (2008) Electrospun submicron bioactive glass fibers for bone tissue scaffold. *J Mater Sci Mater Med* 20(3):793–798
94. Kim H-W, Kim H-E (2006) Nanofiber generation of hydroxyapatite and fluor-hydroxyapatite bioceramics. *J Biomed Mater Res B Appl Biomater* 77B(2):323–328

95. Chen F, Tang Q-L, Zhu Y-J et al (2010) Hydroxyapatite nanorods/poly(vinyl pyrrolidone) composite nanofibers, arrays and three-dimensional fabrics: electrospun preparation and transformation to hydroxyapatite nanostructures. *Acta Biomater* 6(8):3013–3020
96. Tan F, Naciri M, Al-Rubeai M (2011) Osteoconductivity and growth factor production by MG63 osteoblastic cells on bioglass-coated orthopedic implants. *Biotechnol Bioeng* 108(2):454–464
97. Y-c Hu, J-p Z (2009) Osteostimulation of bioglass. *Chin Med J* 122(19):2386–2389
98. White AA, Best SM, Kinloch IA (2007) Hydroxyapatite-carbon nanotube composites for biomedical applications: a review. *Int J Appl Ceram Technol* 4(1):1–13
99. Venugopal J, Prabhakaran MP, Zhang Y et al (2010) Biomimetic hydroxyapatite-containing composite nanofibrous substrates for bone tissue engineering. *Philos Trans R Soc Lond Ser A Math Phys Eng Sci* 368(1917):2065–2081
100. Prabhakaran MP, Venugopal J, Ramakrishna S (2009) Electrospun nanostructured scaffolds for bone tissue engineering. *Acta Biomater* 5(8):2884–2893
101. Zhang H, Liu J, Yao Z et al (2009) Biomimetic mineralization of electrospun poly(lactic-co-glycolic acid)/multi-walled carbon nanotubes composite scaffolds in vitro. *Mater Lett* 63(27):2313–2316
102. Allo BA, Rizkalla AS, Mequanint K (2010) Synthesis and electrospinning of ϵ -polycaprolactone-bioactive glass hybrid biomaterials via a sol–gel process. *Langmuir* 26(23):18340–18348
103. Albrektsson T, Johansson C (2001) Osteoinduction, osteoconduction and osseointegration. *Eur Spine J* 10(Suppl 2):S96–S101
104. Asran AS, Henning S, Michler GH (2010) Polyvinyl alcohol-collagen-hydroxyapatite bio-composite nanofibrous scaffold: mimicking the key features of natural bone at the nanoscale level. *Polymer* 51(4):868–876
105. Kim H-W, Lee H-H, Knowles JC (2006) Electrospinning biomedical nanocomposite fibers of hydroxyapatite/poly(lactic acid) for bone regeneration. *J Biomed Mater Res A* 79A(3):643–649
106. Rai B, Noohom W, Kithva PH et al (2008) Bionanohydroxyapatite/poly(3-hydroxybutyrate-co-3-hydroxyvalerate) composites with improved particle dispersion and superior mechanical properties. *Chem Mater* 20(8):2802–2808
107. Lee HJ, Choi HW, Kim KJ et al (2006) Modification of hydroxyapatite nanosurfaces for enhanced colloidal stability and improved interfacial adhesion in nanocomposites. *Chem Mater* 18(21):5111–5118
108. Chen C-W, Oakes CS, Byrappa K et al (2004) Synthesis, characterization, and dispersion properties of hydroxyapatite prepared by mechanochemical-hydrothermal methods. *J Mater Chem* 14(15):2425
109. Wilson OC Jr (2009) Surface modification of hydroxyapatite: a review. In: Narayan RJ, Kumta PN, Wagner WR (eds) *Advances in biomedical and biomimetic materials*. The American Ceramic Society, Pittsburgh, PA
110. Kurashina K, Kurita H, Wu Q et al (2002) Ectopic osteogenesis with biphasic ceramics of hydroxyapatite and tricalcium phosphate in rabbits. *Biomaterials* 23(2):407–412
111. Norton J, Malik KR, Darr JA et al (2006) Recent developments in processing and surface modification of hydroxyapatite. *Adv Appl Ceram* 105(3):113–139
112. Bhadang KA, Holding CA, Thissen H et al (2010) Biological responses of human osteoblasts and osteoclasts to flame-sprayed coatings of hydroxyapatite and fluorapatite blends. *Acta Biomater* 6(4):1575–1583
113. Arinze T, Tran T, McAlary J et al (2005) A comparative study of biphasic calcium phosphate ceramics for human mesenchymal stem-cell-induced bone formation. *Biomaterials* 26(17):3631–3638
114. Cholewa-Kowalska K, Kokoszka J, Łączka M et al (2009) Gel-derived bioglass as a compound of hydroxyapatite composites. *Biomed Mater* 4(5):055007
115. Boccaccini AR, Gerhardt L-C (2010) Carbon nanotube composite scaffolds and coatings for tissue engineering applications. *Key Eng Mater* 441(31):31–52
116. Meng ZX, Zheng W, Li L et al (2010) Fabrication and characterization of three-dimensional nanofiber membrane of PCL-MWCNTs by electrospinning. *Mater Sci Eng C* 30(7):1014–1021

117. Kang M, Chen P, Jin H (2009) Preparation of multiwalled carbon nanotubes incorporated silk fibroin nanofibers by electrospinning. *Curr Appl Phys* 9(1):S95–S97
118. Yoon OJ, Kim HW, Kim DJ et al (2009) Nanocomposites of electrospun poly[(D, L-lactic)-co-(glycolic acid)] and plasma-functionalized single-walled carbon nanotubes for biomedical applications. *Plasma Process Polym* 6(2):101–109
119. Pantarotto D, Briand J-P, Prato M et al (2004) Translocation of bioactive peptides across cell membranes by carbon nanotubes. *Chem Commun* 10(1):16
120. Zeng H, Gao C, Yan D (2006) Poly(ϵ -caprolactone)-functionalized carbon nanotubes and their biodegradation properties. *Adv Func Mater* 16(6):812–818
121. Sui XM, Giordani S, Prato M et al (2009) Effect of carbon nanotube surface modification on dispersion and structural properties of electrospun fibers. *Appl Phys Lett* 95(23):233113
122. Zhang H, Chen Z (2010) Fabrication and characterization of electrospun p(lga)/mwnts/hydroxyapatite biocomposite scaffolds for bone tissue engineering. *J Bioactive Comp Polym* 25(3):241–259
123. Teo W-E, Ramakrishna S (2009) Electrospun nanofibers as a platform for multifunctional, hierarchically organized nanocomposite. *Compos Sci Technol* 69(11–12):1804–1817
124. Moghe AK, Gupta BS (2008) Co-axial electrospinning for nanofiber structures: preparation and applications. *Polym Rev* 48(2):353–377
125. Townsend-Nicholson A, Jayasinghe SN (2006) Cell electrospinning: a unique biotechnology for encapsulating living organisms for generating active biological microthreads/scaffolds. *Biomacromolecules* 7(12):3364–3369
126. Koyama Y, Mitsui N, Suzuki N et al (2008) Effect of compressive force on the expression of inflammatory cytokines and their receptors in osteoblastic SAOS-2 cells. *Arch Oral Biol* 53(5):488–496
127. Lee YH, Lee JH, An IG et al (2005) Electrospun dual-porosity structure and biodegradation morphology of montmorillonite reinforced PLLA nanocomposite scaffolds. *Biomaterials* 26(16):3165–3172
128. Baker BM, Gee AO, Metter RB et al (2008) The potential to improve cell infiltration in composite fiber-aligned electrospun scaffolds by the selective removal of sacrificial fibers. *Biomaterials* 29(15):2348–2358
129. Guimaires A, Martins A, Pinho ED et al (2010) Solving cell infiltration limitations of electrospun nanofiber meshes for tissue engineering applications. *Nanomedicine* 5(4):539–554
130. Whited BM, Whitney JR, Hofmann MC et al (2011) Pre-osteoblast infiltration and differentiation in highly porous apatite-coated PLLA electrospun scaffolds. *Biomaterials* 32(9):2294–2304
131. Simonet M, Schneider OD, Neuenschwander P et al (2007) Ultraporous 3D polymer meshes by low-temperature electrospinning: use of ice crystals as a removable void template. *Polym Eng Sci* 47(12):2020–2026
132. Leong MF, Rasheed MZ, Lim TC et al (2009) In vitro cell infiltration and in vivo cell infiltration and vascularization in a fibrous, highly porous poly(D, L-lactide) scaffold fabricated by cryogenic electrospinning technique. *J Biomed Mater Res A* 91A(1):231–240
133. Teo WE, Liao S, Chan CK et al (2008) Remodeling of three-dimensional hierarchically organized nanofibrous assemblies. *Curr Nanosci* 4(4):361–369
134. Martins A, Chung S, Pedro AJ et al (2009) Hierarchical starch-based fibrous scaffold for bone tissue engineering applications. *J Tissue Eng Regen Med* 3(1):37–42
135. Soliman S, Pagliari S, Rinaldi A et al (2010) Multiscale three-dimensional scaffolds for soft tissue engineering via multimodal electrospinning. *Acta Biomater* 6(4):1227–1237
136. Kim T, Chung H, Park T (2008) Macroporous and nanofibrous hyaluronic acid/collagen hybrid scaffold fabricated by concurrent electrospinning and deposition/leaching of salt particles. *Acta Biomater* 4(6):1611–1619
137. Wright LD, Andric T, Freeman JW (2011) Utilizing NaCl to increase the porosity of electrospun materials. *Mater Sci Eng C* 31(1):30–36
138. Luong ND, Moon I-S, Nam J-D (2009) A solvent-assisted compression molded of poly(L-lactide)/hydroxyapatite electrospun fibers for robust engineered scaffold systems. *Macromol Mater Eng* 294(10):669–704

139. Shim IK, Jung MR, Kim KH et al (2010) Novel three-dimensional scaffolds of poly(L-lactic acid) microfibers using electrospinning and mechanical expansion: fabrication and bone regeneration. *J Biomed Mater Res B Appl Biomater* 95B(1):150–160
140. Blakeney BA, Tambralli A, Anderson JM et al (2011) Cell infiltration and growth in a low density, uncompressed three-dimensional electrospun nanofibrous scaffold. *Biomaterials* 32(6):1583–1590
141. McCullen SD, Miller PR, Gittard SD et al (2010) In situ collagen polymerization of layered cell-seeded electrospun scaffolds for bone tissue engineering applications. *Tissue Eng Part C Methods* 16(5):1095–1105
142. Kurpinski KT, Stephenson JT, Janairo RRR et al (2010) The effect of fiber alignment and heparin coating on cell infiltration into nanofibrous PLLA scaffolds. *Biomaterials* 31(13):3536–3542
143. Moore K, Macsween M, Shoichet MS (2006) Immobilized concentration gradients of nerve growth factor guide neurite outgrowth. *Tissue Eng* 12(2):267–278
144. Yoo HS, Kim TG, Park TG (2009) Surface-functionalized electrospun nanofibers for tissue engineering and drug delivery. *Adv Drug Deliv Rev* 61(12):1033–1042
145. Park K, Ju YM, Son JS et al (2007) Surface modification of biodegradable electrospun nanofiber scaffolds and their interaction with fibroblasts. *J Biomater Sci Polym Ed* 18(4):369–382
146. Polini A, Pagliara S, Stabile R et al (2010) Collagen-functionalised electrospun polymer fibers for bioengineering applications. *Soft Matter* 6(8):1668
147. Chen J-P, Su C-H (2011) Surface modification of electrospun PLLA nanofibers by plasma treatment and cationized gelatin immobilization for cartilage tissue engineering. *Acta Biomater* 7(1):234–243
148. Kim TG, Park TG (2006) Biomimicking extracellular matrix- cell adhesive RGD peptide modified electrospun poly(D, L-lactic-co-glycolic acid) nanofiber mesh. *Tissue Eng* 12(2):221–233
149. Shin YM, Shin H, Lim YM (2010) Surface modification of electrospun poly(L-lactide-co-ε-caprolactone) fibrous meshes with a RGD peptide for the control of adhesion, proliferation and differentiation of the preosteoblastic cells. *Macromol Res* 18(5):472–481
150. Paletta JRJ, Bockelmann S, Walz A et al (2009) RGD-functionalisation of PLLA nanofibers by surface coupling using plasma treatment: Influence on stem cell differentiation. *J Mater Sci Mater Med* 21(4):1363–1369
151. Casper CL, Yang W, Farach-Carson MC et al (2007) Coating electrospun collagen and gelatin fibers with perlecan domain i for increased growth factor binding. *Biomacromolecules* 8(4):1116–1123
152. Joung YK, Bae JW, Park KD (2008) Controlled release of heparin-binding growth factors using heparin-containing particulate systems for tissue regeneration. *Expert Opin Drug Deliv* 5(11):1173–1184
153. Sun B, Chen B, Zhao Y et al (2009) Crosslinking heparin to collagen scaffolds for the delivery of human platelet-derived growth factor. *J Biomed Mater Res B Appl Biomater* 91B(1):366–372
154. Patel S, Kurpinski K, Quigley R et al (2007) Bioactive nanofibers: synergistic effects of nanotopography and chemical signaling on cell guidance. *Nano Lett* 7(7):2122–2128
155. Kanzaki S, Takahashi T, Kanno T et al (2008) Heparin inhibits BMP-2 osteogenic bioactivity by binding to both BMP-2 and BMP receptor. *J Cell Physiol* 216(3):844–850
156. Zhang H, Migneco F, Lin C-Y et al (2010) Chemically-conjugated bone morphogenetic protein-2 on three-dimensional polycaprolactone scaffolds stimulates osteogenic activity in bone marrow stromal cells. *Tissue Eng Part A* 16(11):3441–3448
157. Luu HH, Song W-X, Luo X et al (2007) Distinct roles of bone morphogenetic proteins in osteogenic differentiation of mesenchymal stem cells. *J Orthop Res* 25(5):665–677
158. Wozney JM (2002) Overview of bone morphogenetic proteins. *Spine* 27(16S):S2–S8
159. David L, Feige J-J, Bailly S (2009) Emerging role of bone morphogenetic proteins in angiogenesis. *Cytokine Growth Factor Rev* 20(3):203–212
160. Nandakumar A, Yang L, Habibovic P et al (2010) Calcium phosphate coated electrospun fiber matrices as scaffolds for bone tissue engineering. *Langmuir* 26(10):7380–7387

161. Cui W, Li X, Xie C et al (2010) Hydroxyapatite nucleation and growth mechanism on electrospun fibers functionalized with different chemical groups and their combinations. *Biomaterials* 31(17):4620–4629
162. Yang F, Wolke JGC, Jansen JA (2008) Biomimetic calcium phosphate coating on electrospun poly(ϵ -caprolactone) scaffolds for bone tissue engineering. *Chem Eng J* 137(1):154–161
163. Chen J, Chu B, Hsiao BS (2006) Mineralization of hydroxyapatite in electrospun nanofibrous poly(L-lactic acid) scaffolds. *J Biomed Mater Res A* 79A(2):307–317
164. Li X, Xie J, Yuan X et al (2008) Coating electrospun poly(ϵ -caprolactone) fibers with gelatin and calcium phosphate and their use as biomimetic scaffolds for bone tissue engineering. *Langmuir* 24(24):14145–14150
165. Cui W, Li X, Xie C et al (2010) Controllable growth of hydroxyapatite on electrospun poly(dl-lactide) fibers grafted with chitosan as potential tissue engineering scaffolds. *Polymer* 51(11):2320–2328
166. Gupta D, Venugopal J, Mitra S et al (2009) Nanostructured biocomposite substrates by electrospinning and electrospraying for the mineralization of osteoblasts. *Biomaterials* 30(11):2085–2094
167. Jaworek A, Krupa A, Lackowski M et al (2009) Nanocomposite fabric formation by electrospinning and electrospraying technologies. *J Electrostat* 67(2–3):435–438
168. Francis L, Venugopal J, Prabhakaran MP et al (2010) Simultaneous electrospin-electrosprayed biocomposite nanofibrous scaffolds for bone tissue regeneration. *Acta Biomater* 6(10):4100–4109
169. Tsai W-B, Chen RP-Y, Wei K-L et al (2010) Modulation of RGD-functionalized polyelectrolyte multilayer membranes for promoting osteoblast function. *J Biomater Sci Polym Ed* 21(3):377–394
170. Tang Z, Wang Y, Podsiadlo P et al (2006) Biomedical applications of layer-by-layer assembly: from biomimetics to tissue engineering. *Adv Mater* 18(24):3203–3224
171. Tryoen-Th P, Vautier D, Haikel Y et al (2002) Viability, adhesion, and bone phenotype of osteoblast-like cells on polyelectrolyte multilayer films. *J Biomed Mater Res* 60(4):657–667
172. Lochmann A, Nitzsche H, von Einem S et al (2010) The influence of covalently linked and free polyethylene glycol on the structural and release properties of rhBMP-2 loaded microspheres. *J Control Release* 147(1):92–100
173. Crouzier T, Ren K, Nicolas C et al (2009) Layer-by-layer films as a biomimetic reservoir for rhBMP-2 delivery: controlled differentiation of myoblasts to osteoblasts. *Small* 5(5):598–608
174. Quinn A, Such GK, Quinn JF et al (2008) Polyelectrolyte blend multilayers: a versatile route to engineering interfaces and films. *Adv Func Mater* 18(1):17–26
175. Pytlík R, Stehlík D, Soukup T et al (2009) The cultivation of human multipotent mesenchymal stromal cells in clinical grade medium for bone tissue engineering. *Biomaterials* 30(20):3415–3427
176. Jayasinghe SN, Townsend-Nicholson A (2006) Stable electric-field driven cone-jetting of concentrated biosuspensions. *Lab Chip* 6(8):1086–1090
177. Ward E, Chan E, Gustafsson K et al (2010) Combining bio-electrospraying with gene therapy: a novel biotechnique for the delivery of genetic material via living cells. *Analyst* 135(5):1042
178. Yang X, Shah JD, Wang H (2009) Nanofiber enabled layer-by-layer approach toward three-dimensional tissue formation. *Tissue Eng Part A* 15(4):945–956